

PRODUCT DATA SHEET

SCHTUK Extreme White

A ONE PART, CHEMICALLY CURING SOLVENT FREE SEALANT AND ADHESIVE BASED ON HYBRID POLYMER TECHNOLOGY

PRODUCT DESCRIPTION

SCHTUK EXTREME White, based on hybrid polymer technology is the ultimate combined building adhesive and sealant, with the most Extreme power to both bond and seal virtually EVERYTHING to ANYTHING in virtually all conditions, even under water or in the rain!

SCHTUK EXTREME Crystal Clear offers almost limitless benefits as an adhesive and a sealant removing the previous application barriers associated with conventional products.

USES

Sealing and bonding in almost every application imaginable. The following are just some examples:

- As a high quality nail replacement adhesive, even to damp surfaces.
- External and internal perimeter pointing around doors and windows.
- Bonding mirrors to most common substrates.
- Sealing vertical expansion joints.
- Jointing cladding panels.
- Any application requiring high performance, durable sealing and bonding of joints.
- Applications where resistance to chemical spillage is required.

CHARACTERISTICS / ADVANTAGES

- Incredible initial grab, no slip and gap filling properties.
- High bonding strength
- Interior and Exterior Use
- Certified to the harmonized European standard for Sealants for façade and sanitary use.
- Can be applied to Wet Surfaces
- Waterproof & Weatherproof
- Quick Curing.
- Solvent Free
- Resistant to temperature extremes -40°C to +70°C

- Resistant to Chemicals & Petrol (10% dilute acids/alkalis, most solvents)
- Excellent primer less adhesion to most surfaces, including metals, most plastics, glass, concrete, plaster, plasterboard, polyester, Perspex, glass, wood, enamel, painted surfaces etc etc.

Skimming Time 15-30 mins
Cure Time ~2mm per 24 hours in depth

Application Temperature +5 to 40°C
Resistant To Slump <3mm (ISO7390)
Overpaintability Overpaintable with some paints - always test a small area first

Cleaning Uncured product: white spirits
Cured product: mechanical removal

Max Joint Width 25mm

Min Joint Width (in sealing applications as a movement joint) 5mm

APPROVALS / STANDARDS

CE Marked to EN15651-1: 2012, Type F EXT-INT Class F20LM CC and EN15651-3:2012, Type S Class XS2.

PRODUCT INFORMATION

Packaging	290ml Cartridge (Details of Easi Squeeze Stixall Clear covered in Stixall PDS)
Colour	White
Shelf Life	Cartridge: 12 months. Squeezy Tube: 24 months.
Storage Conditions	Store in cool dry conditions between + 5°C and 25°C.
Density	~ 1.05g/cm ³

TECHNICAL INFORMATION

Shore A Hardness	40±5
Elongation at Break	>150% (ISO8339)
Service Temperature	-40 to +70°C

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

All surfaces must be clean and dust free. Surfaces may be damp, but have no standing water. Can be used under water but adhesion performance is reduced so should be applied as an emergency repair in these conditions only.

APPLICATION METHOD / TOOLS

As a nail replacement (panel) adhesive.

- Surfaces must be sound, clean, dry and free from dust, grease, loose material etc.
- Prime dusty surfaces with Everbuild PVA Bond diluted 1:4 with water and allow to dry.
- Apply using a standard sealant gun, cut tip of cartridge, apply nozzle and cut an opening to suit the required bead size.
- For bonding heavy items (Plasterboard/worktops/wall panels etc) apply adhesive all the way around the edge of the item (30-50mm from edge) and cover back with beads of adhesive at 300mm intervals. Alternatively, apply adhesive direct to battens and press into place.
NOTE. With heavy items, always provide temporary support until the adhesive dries.
- For bonding lightweight items (covings, dado rails, skirting etc) apply adhesive to back of item in one or two continuous beads and press immediately into place.
- Where gap filling is required, mark the areas where there is a large gap and apply a thicker bead to these areas.
- In all cases, clean up excess adhesive immediately with a cloth/white spirits.

As a sealant

Certified to EN15651 Façade for interior, exterior and cold climate applications and for sanitary applications. Reference should be made to the recommended joint ratios. If necessary reduce joint depth using Everbuild Expanding Foam, or Joint backer rod. Furthermore, ensure that the joint design only permits adhesion to two surfaces, as three sided adhesion will impair flexibility.

Where the sealant is used in a joint configuration, masking tape should be used to prevent contamination of adjacent substrates, and ensure a neat sealing line. Masking tape should be removed immediately after tooling. The joint should be tooled within 5 minutes of application to ensure good contact between the sealant and the substrate. Tooling of the sealant also gives a smooth, professional finish.

Fixing mirrors

Apply 6mm diameter beads of sealant direct to back of mirror in vertical strips, spaced at 30-40mm centers. Immediately place mirror in position and secure with good, even pressure with a slight twist action. Provide temporary support (tape) until adhesive has dried (24-48 hours). If required, Stixall may also be used to seal around mirror 24 hours after fixing (to allow for cure) Uncured material can be removed by wiping with a dampened cloth with white spirit. Cured material can be carefully removed by mechanical means. Full cure must be allowed before over painting.

CLEANING OF TOOLS

Uncured product: white spirits.

Cured product: mechanical removal.

LIMITATIONS

- Use on overhead applications – Always use in conjunction with mechanical fixings.
- Use in conjunction with mechanical fixings for glass block fitting or large mirrors (>0.5m² total area).
- For heavy items, provide temporary support until adhesive has dried.
- In areas of high UV; some darkening/discolouration may occur. This does not affect the performance of the sealant.
- Do not seal mirror edges/plastic sheeting until adhesive has cured.
- Overpaintability: check compatibility with specific paint first before over painting large areas.
- Do not use on surfaces that bleed oils or plasticizers.
- It is the user's responsibility to determine suitability for use. If in doubt, please contact Technical Services Department for advice.

- Not for use as part of a structural glazing system.
- Not for use in aquarium manufacture. Use AQUA MATE.
- Not for use in conjunction with bitumen, or asphalt. Use WEATHER MATE.
- Do not use in conjunction with undiluted bleach, this can cause discoloration of product.
- Not suitable for use in or around chlorinated water.
- Yellowing can occur in the dark.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



1st Floor
19 Clifftown Road
Southend-On-Sea
SS1 1AB

Tel 0844 887 1401

www.strongfastglobal.com

Pinnacle House,
Newtown Cross,
The Ward,
Co. Dublin,
D11 K27C

Tel 0800 970 2414